

Thaicast S1

APPLICATION - Sanitaryware

CHEMICAL ANALYSIS (%)	Min.	Value	Max.
SiO ₂	61.0	63.0	65.0
Al ₂ O ₃		22.8	
Fe ₂ O ₃	0.0	1.70	2.20
TiO ₂		0.67	
CaO		0.23	
MgO		0.60	
K ₂ O	2.05	2.25	2.45
Na ₂ O		0.21	
LOI	8.0	9.0	10.0

RESIDUE – WET sieve (mass %)

> 125 µm			3.00
> 45 µm		4.50	

PARTICLE SIZE ANALYSIS–Sedigraph (cumulative mass %)

< 5 µm	80	85	90
< 2 µm	65	70	75
< 1 µm	50	55	60
< 0.5 µm	40	45	50

PHYSICAL PROPERTIES

Methylene Blue Index (mg.g ⁻¹)	35.0	39.0	43.0
Water soluble salts(ppm)		950	
Water soluble sulphate(ppm)	200	400	600
Moisture content (%)			15.0

CASTING DATA

Deflocculant demand (wt%)	0.35	0.60	0.85
Cast rate (mm. in 30 minutes)	5.0	6.3	7.5

MODULUS OF RUPTURE (as 100% clay)

Dried at 110 °C (Kgf.cm ⁻²)	60.0	70.0	80.0
---	------	------	------

FIRED PROPERTIES

	1240°C		
L*		66.73	
a*		1.65	
b*		13.18	
Contraction (%)		9.2	
Water absorption (%)		0.10	

PRODUCT FORM & STANDARD PACKAGING

Shredded, Noodle or Cake
Big bag, 50 kg bags, bulk

BCS 001 15 April 2020

© Imerys Ceramics 2020

Issue No. 06 Edition

This version supersedes BCS001

Issue No. 05 Date : 30/10/2013

Sales Office

Imerys Ceramics Thailand
228 Vibhavadi Rangsit Road,
Din Dang, Bangkok, Thailand

Tel. +66 269 50 999

Fax: +66 269 50 901

www.imerys-ceramics.com

Max, Min values are specified properties.
All other values are typical. The data quoted are determined by the use of Imerys Standard Test Methods, copies of which will be supplied on request. Every precaution is taken in production to ensure the products conform to our published data. Since the products are based on naturally occurring materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our "Conditions of Sales" copies of which will be supplied on request.